

EXTRUSION INGOTS



Chemical composition for some typical alloys

Alloy	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Other	Total other
606035	0.40-0.45	0.18-0.23	0.03	0.03	0.45-0.50	0.02	0.03	0.02	0.02	0.10
606090	0.50-0.55	0.18-0.23	0.03	0.03	0.50-0.55	0.02	0.03	0.02	0.02	0.10
600540	0.58-0.63	0.18-0.23	0.10-0.20	0.12-0.20	0.53-0.58	0.08	0.03	0.02	0.02	0.10
608250	0.95-1.05	0.15-0.25	0.03	0.50-0.57	0.63-0.70		0.03	0.02	0.02	0.10